

RHEOFINISH®

225 P

(Replaces Atrorelease)

Water dispersible chemical release agent**Description**

A ready to use water dispersible, safe, effective release agent which is friendly to the environment. RHEOFINISH 225 P is applied to mould and shutter faces prior to casting concrete in order to achieve a clean release. After removal of the formwork, the resultant concrete has a smooth, hard, uniform finish, with reduced incidence of blow holes. RHEOFINISH 225 P can be diluted 1 to 1 by water and applied to the formwork by spray in the form of a light uniform mist coating.

Primary uses

RHEOFINISH 225 P is formulated for application to plywood, timber, steel and plastic faced formwork and moulds, prior to casting concrete, to ensure a clean release.

Packaging

RHEOFINISH 225 P is available in 20 and 210 litre drums. Bulk deliveries available upon request.

Typical properties*

* Properties listed are only for guidance and are not a guarantee of performance.

Colour	Amber
SG finished product	0.85 –0.87 at 25°C
Chloride content:	Nil

Composition

A chemically active release agent blended with water.

Directions for use

Apply before the first casting and thereafter re-apply immediately after stripping and cleaning the mould.

Lightweight horticultural sprayers are ideal as RHEOFINISH 225 P is finely atomised to give a uniform coating. Excessive application should be avoided.

Alternatively, application may be made by a fine haired brush, only a very thin coating should be made and any excess removed.

If after the first application, the RHEOFINISH 225 P is completely absorbed into new timber or plywood, a further application should be made before filling the moulds or formwork.

Action

RHEOFINISH 225 P reacts chemically with cement to impart excellent release properties to treated surfaces. Concrete cast against surfaces coated with RHEOFINISH 225 P exhibit a smooth, hard, uniform finish.

RHEOFINISH 225 P has no negative effect on the properties of concrete nor will it impair the adhesion of subsequent surface treatments when applied at the recommended coverage rates.

Coverage

The coverage rate for RHEOFINISH 225 P is between 30 to 40m²/litre when spray applied depending on smoothness and porosity of the formwork used. Coverage is considerably enhanced on marine ply and steel faced forms.

Note:

Progressively better results are obtained on plywood and timber moulds as they become impregnated and the operatives become accustomed to working with the release agent. RHEOFINISH 225 P in general, may be used over timber moulds etc., which have been treated with other mould oils, providing excess has been removed.

Equipment care

RHEOFINISH 225 P may usually be left in spray guns or sprayers without detriment, but with certain types, there may be some softening of rubber seals with prolonged contact.

Storage

Store under cover, out of direct sunlight and protect from extremes of temperature. Storage life up to 1 year when stored in unopened containers as above. The product must be stirred before being used.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult Degussa's Technical Services Department.

Safety precautions

As with all chemical products care should be taken during use and storage to avoid contact with eyes and mouth. Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. Keep away from children and animals. Reseal containers after use.

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Degussa representative. Degussa reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality

All products produced by Degussa certified manufacturing facilities, are produced to conform to systems designed to meet internationally recognised quality standards.

04/2006 Degussa-IR